



Legend™ LHS Premium Ladder Heatshrink

The Silver Fox Legend™ Premium heatshrink tubing is manufactured to offer a consistently high grade Heatshrink solution. The ladder format enables the user to easily remove the markers from the carrier

Supplied in a ladder format, the Silver Fox Legend® LHS Premium Ladder Heatshrink is manufactured in a 3:1 ratio.

Print in conjunction with our DTP-1/300 Plug'N'Play thermal printer with the same ribbon as all our other thermal labels.

TECHNICAL DATA

Printing method:	DTP-1 Printer
Thermal Ribbon:	TSR3
Material:	Polyolefin
Shrink Ratio:	3-1
Min. shrink temp:	90°C
Dielectric Strength:	≥ 37 kV/mm
RoHS:	Yes
Reach:	Yes

TESTING

Test	Method
UV Weathering	ISO 4982 Part 3 Method A Cycle 1 – 3000 hrs
Elevated Temperature**	MIL-STD-202G Method 108A – 2000 hrs @ 70°C to 100°C
Low Temperature*	MIL-STD-810 Method 502.4 – 72 hrs @ 40°C
H2S Sour Gas	Exposure (2% H2S)
Salt Mist Spray	EC60068-2-52 Test kb Salt Mist (Cyclic)
Resistance to Solvents	MIL-STD-202-215 w/change 1

* Followed by a manipulation test. Manipulation of the labels were performed at -40°C at completion of the low temperature test.

**Samples were subjected to 500 hours @ 70°C followed by 500 hours @ 85°C followed by 1000 hours @100°C





Legend™ LHS Premium Ladder Heatshrink

Additional Information

Use with Silver Fox Labacus® Innovator Advanced or Professional software. Print in conjunction with our Fox-in-a-Box® Plug'N'Play thermal printer using the same ribbon as all our other thermal labels.

ORDER INFORMATION

Product Code	Cable ID Ø	Cable ID Ø	Labels	Pack	Colour
	Exp. (mm)	Rec. (mm)	per roll	Qty	
LHS/L50/3-1.T(PF)	3	1	2500	1 Roll	○ ●
LHS/L50/4.8-1.6T(PF)	4.8	1.6	2000	1 Roll	○ ●
LHS/L50/6-2T(PF)	6	2	1500	1 Roll	○ ●
LHS/L50/12-4T(PF)	12	4	900	1 Roll	○ ●
LHS/L50/24-8T(PF)	24	8	375	1 Roll	○ ●
LHS/L50/39-13T(PF)	39	13	275	1 Roll	○ ●

STORAGE INSTRUCTIONS

Storage Instructions	Store between 50°F (10°C) and 77°F (25°C)
Conditions	Keep in dark conditions
Humidity Resistance	35% to 65% RH

Disclaimer: The information contained in this datasheet is based on data we believe to be reliable and is given for information only and without guarantee and does not constitute a warranty. We are not able to anticipate every set of conditions, so always suggest that users should also satisfy themselves as to the suitability of our products for their particular environment and application and not make any assumptions based on information in this data sheet that is included or omitted. This datasheet supersedes any previous information/datasheet released and is subject to change without notice.